



Analysis of Efficiency and Thermal Withstanding Capacity of Single Phase Induction Motor Coated with Al₂O₃ Nano Filler Mixed Enamel

Lieutenant.J. Ganesan¹, D. Edison Selvaraj², B. GuruPrakash³, R. Vishnu Prakash⁴, E. Muthupandi⁵, R. Balakumar⁶

Assistant Professor, Department of EEE, SreeSowdambika College of Engineering, Aruppukkotai, India¹

Assistant Professor, Iyer Language and Academic Classes, Mumbai, India²

BE – IV year, Department of EEE, Mepco Schlenk Engineering College, Sivakasi, India^{3,4,5,6}

ABSTRACT: It has been found that the addition of nanofillers to the enamel can greatly improve the thermal, mechanical and electrical properties of enamel. Al₂O₃ has been used as nano filler. The micro particles of Al₂O₃ were converted into nano particles with the help of ball mill. Scanning electron microscope (SEM) has been used to augment the particle size of the nano powder. The nano filler was mixed with enamel by using ultrasonic vibrator. The enamel filled with nano filler was coated on the windings of the single phase induction motor. The performance analysis of the single phase induction motor was carried out by no load test, blocked rotor test and load test. Based on the calculations and result obtained by the above tests, the efficiency of the induction motor coated with enamel filled with nano filler of Al₂O₃ was increased by 6% when compared to that of induction motor coated with pure enamel. Heat run test was also performed on this motor to determine the total loss of energy dissipated as heat.

Key words – Single Phase Induction motor, Enamel, Coating, Nano Filler, Load Test, Al₂O₃

I. INTRODUCTION

In recent days, a great deal of attention has been given to the applications of nano fillers in the field of electrical insulating materials. It has been noted that the use of nano fillers to the enamel can greatly improve the thermal, mechanical and electrical properties of it. Single phase Induction motors are widely used in fans, centrifugal pumps, blowers, lifts, washing machines, hair driers, toys and so on. The efficiency of the induction motor depends upon the enamel used. For motors, the enamel was used for three purposes: impregnation, coating and adhesion. The efficiency of the induction motor could be increased by adding the nano fillers with the enamel which was used as coating for the windings of the motor. In this paper, the efficiency of the normal single phase induction motor and Al₂O₃ nano filler added enamel coated with the single phase induction motor was analyzed and the results were compared with each other. Heat run tests were performed on electric machines to determine the total loss of energy dissipated as heat. It was a well-known fact that the operating temperature of an electric machine has a very strong relationship with the life duration of the insulation. The enamel used for coating the machine windings were organic in nature and were adversely affected by thermal decomposition.

II. COATING OF THE NANO FILLER ADDED ENAMEL TO THE WINDINGS OF THE MOTOR

Five percentage of nano powder of Al₂O₃ was taken and it was mixed with the enamel by using ultrasonic vibrator. Then this enamel was coated on the windings of the single phase induction motor. The specifications of the single phase induction motor were shown below in the table I.

TABLE I SPECIFICATIONS OF THE SINGLE PHASE INDUCTION MOTOR

Quantity	Rating
Power	1.5 HP
Speed	1470 rpm
Current	4 A
Voltage	220



III. EXPERIMENTAL ANALYSIS

A. PERFORMANCE ANALYSIS OF SQUIRREL CAGE INDUCTION MOTOR – DIRECT LOADING METHOD

The load test was conducted as per the circuit diagram shown in the figure 1 and the output power ,current, efficiency, powerfactor and speed of the induction induction was measured. The maximum efficiency obtained from an ordinary induction motor was 69%. The maximum efficiency obtained from nano coated induction motor was 75%.




Fig 1 circuit diagram for load test on single phase induction motor

B. TEMPERATURE TEST

Heat run test was performed on electric machines to determine the total loss of energy dissipated as heat. It was a well-known fact that the operating temperature of an electric machine has a very strong relationship with the life duration of the insulation. Heat run tests were conducted on this motor as per IEC 60851. The temperature of the motor was measured under different conditions and the readings were shown in the table II.

TABLE II MEASUREMENT OF TEMPERATURE

Time	Normal motor	Nano coated motor
0	30	30
5	44	40
10	48	43
15	50	46
20	53	49
25	55	50
30	57	53
35	58	53

IV. CONCLUSIONS

The following observations were clear as per this study:

1. The efficiency of the induction motor was increased by 6 % by adding nano filler of Al₂O₃ to the enamel used as the coating for the windings of the single phase induction motor.
2. The addition of nano fillers to the enamel has increased the temperature withstanding capacity of the induction motor. Hence the life time of the motor will be increased.



V. ACKNOWLEDGEMENT

Thank God and His almighty power to finish His research work by using me, my project guide and my students for His ultimate work.

REFERENCE

1. Selvaraj, D. Edison. "Characterization of dielectric properties of the enamel filled with carbon nanotubes for the frequency range of 50 Hz-5 MHz." *International Journal of Science and Engineering Applications* 1.2 (2012): 102-106.
2. Selvaraj, D. Edison, and C. PugazhendhiSugumaran. "Comparative Analysis of Dielectric Properties of Enamel Filled with Various Nanofillers such as ZrO₂, Al₂O₃, CNT and ZnO." *International Journal of Science and Engineering Applications* 1.1 (2012): 51-55.
3. Selvaraj, D. Edison. "Partial discharge characteristics of enamel filled with micro and nano composite of SiO₂ and TiO₂." *International Journal of Science and Engineering Applications* 1.2 (2012): 95-101.
4. Selvaraj, D. Edison, et al. "Analysis of Efficiency, Thermal Withstanding Capacity and Electromagnetic Interference of Three Phase Squirrel Cage Induction Motor Coated with SiO₂ & TiO₂ NanoComposite Filled Enamel." *International Journal of Science and Engineering Applications* 1.1 (2012): 17-21.
5. Edison Selvaraj, D., C. PugazhendhiSugumaran, and A. SivaPrakash. "Characterization of Electrical and Thermal Properties of Enamel Filled with Carbon Nanotubes." *Proceedings of the Third International Conference on Trends in Information, Telecommunication and Computing*. Springer New York.

BIOGRAPHY



Lieutenant. J. Ganesan received the B.E., degree in Electrical and Electronics Engineering from Anna University, Chennai in 2007 and doing M.E part time in Applied Electronics at Anna University of Technology, Tirunelveli, Tamilnadu, India. Presently he is working as Assistant Professor in the Department of Electrical and Electronics Engineering, SreeSowdambika College of Engineering, Aruppukottai.



Mr. D. Edison Selvaraj received the B.E. degree in Electrical and Electronics Engineering from Anna University, Chennai in 2007 and M.E. degree in High-Voltage Engineering from Anna University, Chennai, TamilNadu, India in the year 2010. Presently, he is working as Assistant Professor in the Department of Electrical and Electronics Engineering, MepcoSchlenk Engineering College, Sivakasi.



B.Guru prakash, He is pursuing B.E degree in EEE in MepcoSchlenk Engineering College, Sivakasi.



E.Muthupandi, He is pursuing B.E degree in EEE in MepcoSchlenk Engineering College, Sivakasi.



R. Vishnu Praksah, He is pursuing B.E degree in EEE in MepcoSchlenk Engineering College, Sivakasi.



R. Balakumar, He is pursuing B.E degree in EEE in MepcoSchlenk Engineering College, Sivakasi.